XL-CS-31 OA/SA is suitable for build up of carbon and low alloy steel parts and a good base for hardfacing. It gives crack free deposits on tractor rollers. idlers, and rails. Especially suitable for multiple layers. Use UV-A flux.				
APPLICATIONS Tractor Parts, Crane Wheels, Mine Car Wheels, Table Mill Rolls, Shovel Parts etc				

<u>ALLOY CONTENT</u> C, Mn, Si, Mo	
HARDNESS IN HRC	red
28-30	

RECOMMENDED OPERATING PARAMETERS

Diameters (In mm)	2.40	2.80
Current (In Amps)	250-300	300-350
Voltage (V)	26-32	26-32
Stick out (In mm)	30-40	30-40

Power Source: Constant Potential DC+ve

PACKING DATA

Standard wires diameters: 2.40mm, 2.80mm Supplied in 12.5 Kgs / 15 Kgs layer wound vacuum packed plastic spool or in 125 Kgs / 250 Kgs corrugated drums.

Also available in 1.20mm/1.60mm/2.00mm diameters and other type of packaging on request.

Wearresist Technologies Pvt. Ltd.

749/9 GIDC, Makarpura Baroda: 390 010 Gujarat, INDIA Ph: +91 – 265 – 2634734, 2651548 Fax: +91 – 265 – 2649085 e-mail: <u>custsupport@wearresist.com</u> Web: www.wearresist.com

